

# Technical Data Sheet

## Alberdingk® AC 25381

### Characteristic

Alberdingk® AC 25381 is a multiphase, self-crosslinking acrylic dispersion. It has excellent exterior durability, very good block resistance, high gloss and low water absorption.

### Features:

Very good chemical resistance  
Excellent wet adhesion  
Superior water resistance

### Specification:

NVW	%	47.0 – 49.0
pH value		7.5 – 8.5
Viscosity	cps	2000 - 8000

### According to:

DIN EN ISO 3251  
1.0 g weighed quantity at 105°C  
DIN ISO 976  
ISO 1652, Brookfield RVT  
Spindle 1/rpm 20/factor 5

### Further typical data\*:

MFFT	°C	approx. 17
Koenig hardness	s	approx. 65

### Applications:

Low VOC enamels  
Exterior wood coatings  
Parquet varnishes  
Furniture coatings  
KCMSA coatings

# Technical Data Sheet

## Alberdingk<sup>®</sup> AC 25381

### Storage:

In originally closed containers ALBERDINGK-dispersions are stable when stored at 20°C for 6 months. The recommended temperature-range for storage is 5 - 30°C. Freezing or storage at higher temperatures than 30°C, can affect the viscosity or the average particle size and finally lead to a sedimentation or coagulation. A contamination with bacteria, fungi or algae can damage the product irreversibly.

ALBERDINGK BOLEY Inc. assures, that the data mentioned under "specification" are stable for 6 months after delivery date, if the product is stored under the recommended conditions. A longer storage does not mean that the product is not usable anymore, but we recommend to check the specification data before use. A warranty after 6 months of storage can not be given by ALBERDINGK BOLEY Inc.

### Packaging:

drums (460 lbs)  
totes (2205 lbs)  
as bulk in tank cars, by agreement.

### Safety:

For further information on product safety please refer to the actual material safety data sheet.

### Notice:

\* General information - the values can not be considered as part of the product specification.